

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08K 5/00, 5/12, 5/20, C07C 69/017</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/52089</b> <b>(43) International Publication Date:</b> 8 September 2000 (08.09.00)
<b>(21) International Application Number:</b> PCT/EP99/01429 <b>(22) International Filing Date:</b> 5 March 1999 (05.03.99) <b>(71) Applicant (for all designated States except US):</b> UNIVERSITÄT BAYREUTH [DE/DE]; Universitätsstrasse 30, D-95440 Bayreuth (DE). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> SCHMIDT, Hans-Werner [DE/DE]; Lisztstrasse 26, D-95444 Bayreuth (DE). SCHILDBACH, Thomas [DE/DE]; Egerländerstrasse 8, D-95505 Immenreuth (DE). <b>(74) Agent:</b> RICKER, Mathias; Bardehle, Pagenberg, Dost, Altenburg, Geissler, Isenbruck, Galileiplatz 1, D-81679 München (DE).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> NUCLEATORS FOR CRYSTALLIZABLE THERMOPLASTIC POLYMERS  <b>(57) Abstract</b>  Disclosed are compositions comprising nucleators for crystallizable thermoplastic polymers and, in particular, chemical compounds used as nucleators that comprise moieties that are capable of forming intermolecular hydrogen bonds and that are thermally stable, and the use thereof.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## Nucleators For Crystallizable Thermoplastic Polymers

This invention relates to compositions comprising nucleators for crystallizable thermoplastic polymers and in particular to nucleators that comprise moieties that are capable of forming intermolecular hydrogen bonds and that are thermally stable, and to the use thereof.

Nucleating agents and clarifiers are commonly used in industrial practice in combination with crystallizable thermoplastic polymers to reduce processing cycle times or to impart improved physico-chemical characteristics, such as various optical and mechanical properties, as well as to reduce mold shrinkage. Elaborate lists of nucleating agents and clarifiers can be found in, for example, US Pat. No. 3,367,926, *Plastics Additives Handbook* (4th Ed. Hanser, Munich, 1990, p. 863). Typical nucleating agents known in the art are metallic salts of aliphatic or aromatic carboxylic acids, aromatic salts, metallic salts of aromatic phosphorus compounds, quinacridones, pigments, polymers having melting points, highly branched polymers containing dendritic branches (dendrimers), and minerals such as chalk, gypsum, clay, kaolin, mica, talc and silicates, as well as combinations thereof (US Pat. Nos. 5,278,216; 5,137,973; 4,749,736; 4,694,064; 4,338,228; 3,852,237; U. Johnsen and K.-H. Moos, *Angew. Makromol. Chem*, vol. 74, p. 1 (1978); A. Wlochowicz and M. Eder, *Angew. Makromol. Chem*, vol.

171, p. 79 (1989); H. N. Beck, J. Appl. Polym. Sci., vol. 11, p. 673 (1967); F. L. Binsbergen, Polymer, vol. 11, p. 253 (1970)). In addition, German Offenlegungsschrift 1951 632 discloses the use of solid, crystalline aromatic  
5 carboxilicimide-diphthalimides and N-substituted aromatic carboxylic imide-diphthalimides.

More recently developed nucleating agents and clarifiers dissolve in the polymer melt (R. Schlotmann and R. Walker, Kunststoffe, vol. 86, p. 1002 (1996)), which  
10 was found to be effective for improving dispersion of these additives. Most popular have become compounds that are based on D-sorbitol, which belongs to the general chemical family of carbohydrates, that is defined as polyhydroxy aldehydes, polyhydroxy ketones, or compounds  
15 that can be hydrolyzed to them (R. T. Morrion and Robert Neilson Boyd, Organic Chemistry, 2nd. Ed., (Allyn and Bacon, Inc., Boston), 1966, p. 983). There are several commercial nucleators based on sorbitol including 1,3-2,4-di(benzylidene)-D-sorbitol (Millad 3905, Milliken Chemical  
20 Co.); 1,3-2,4-di(4-tolylidene)-D-sorbitol (Millad 3940, Milliken Chemical Co.); 1,3-2,4-di(4-ethylbenzylidene)-D-sorbitol (N-4, Mitsui Petrochemical Industries, Ltd.). US Pat. Nos. 5,574,174; 5,198,484; and WO 95/13317 disclose the preparation and use of sorbitol derivatives. US Pat.  
25 No. 4,294,747 discloses polyhydric alcohol acetals of benzaldehyde and derivatives thereof. US Pat. No. 5,216,051 describes triacetal polyol compounds. Use of dibenzylidene sorbitol (US Pat. No. 4,016,118) in

combination with phenyl phosphate compounds is disclosed in US Pat. No. 4,585,817.. Despite wide-spread commercial application, there exist a number of difficulties that are associated with carbohydrate-based compounds as nucleating  
5 and clarifying agents. First, the preparation and purification of sorbitol-based nucleating agents is cumbersome. Another of the well-known difficulties associated with the use of sorbitol clarifying agents in, for example, polyolefins resins is the formation of small  
10 bubbles in articles fabricated from these resins, which appear as white points (US Pat. No. 5,198,484). Finally, among other disadvantages is their unsatisfactory temperature stability that, unfortunately, is inherent to this class of materials.


15           Thus, a need continues to exist for effective nucleating agents that are useful to enhance processing and physico-chemical properties of thermoplastic polymers.

          Now, it has been discovered that certain organic compounds that comprise moieties that are capable of  
20 forming intermolecular hydrogen bonds are effective nucleating agents for crystallizable thermoplastic polymers, provided that those compounds also comprise moieties that are compatible with the thermoplastic polymer.

25           Thus, the present invention relates to compositions which comprise:

(i) one or more nucleators that comprise moieties that are capable of forming intermolecular hydrogen bonds; and

(ii) one or more crystallizable thermoplastic polymers, which may optionally include common additives and fillers. Particularly, the present invention relates to A composition comprising (i) a crystallizable thermoplastic polymer and (ii) one or more nucleators of the formula



wherein:

x is an integer from two to seven;

y is an integer from zero to four;

z is an integer from zero to four;

the sum  $x + y + z$  equals an integer from three to seven;

m is an integer from one to three;

and wherein A is a center that is covalently bonded with moieties B, B' or X', or combinations thereof; wherein said moieties B and B' comprise at least one unit capable of forming one or more intermolecular hydrogen bonds; wherein moieties X and X' are compatible with said crystallizable thermoplastic polymer; and wherein X is

covalently bonded to B.

Another aspect of the present invention relates to compositions of a crystallizable thermoplastic polymer and a nucleator that comprises moieties that are capable  
5 of forming intermolecular hydrogen bonds and moieties that are compatible with the crystallizable thermoplastic polymer.

Another aspect of the present invention relates to compositions of a crystallizable thermoplastic polymer  
10 and a nucleator that are characterized in that, upon cooling from the melt, their peak temperature of crystallization is at least about 3 °C higher than the peak temperature of crystallization of the neat -that is nucleating agent free- thermoplastic polymer.

15 Still another aspect relates to compositions of a crystallizable thermoplastic polymer and a nucleator that are characterized in that, after cooling from the melt, the size of the spherulites in the crystallized polymer is less than 50 % of the size of the spherulites  
20 in the neat crystallized thermoplastic polymer.

Still yet another aspect of the present invention relates to compositions of a crystallizable thermoplastic polymer and one or more nucleators that are of reduced haze when compared to the neat crystallized  
25 thermoplastic polymer.

Yet another aspect of the present invention relates to compositions of a crystallizable thermoplastic

polymer and one or more nucleators that are of enhanced thermal stability.

Still other aspects of the present invention relate to a novel process for enhancing the rate of crystallization of a melt of a crystallizable thermoplastic polymer, which comprises adding to said melt an effective amount of the nucleators of this invention, and to products made according to that novel process.

Still yet another object of the present invention is to provide products made from crystallizable thermoplastic polymers that comprise an effective amount of the nucleators of this invention.

Advantages that flow from the present invention include a reduction of the processing times of crystallizable thermoplastic polymers. Moreover, the polymers formed in accordance with this invention are characterized by relatively improved thermal, optical and/or mechanical properties. Additional objects, advantages and novel features of the present invention will be set forth in the description that follows, and in part will become apparent to those skilled in the art on examination of the following , or may be learned by practice of the invention. The objects and advantages of the invention may be realized and attained by means of the instrumentalities and combinations particularly pointed out in the appended claims.

The invention will be more fully understood and further advantages will become apparent in the following detailed description of the invention and the accompanying drawings in which:


5           FIG. 1 is an optical photomicrograph of a film of isotactic polypropylene which does not contain a nucleating agent. The film was compression molded at 210 °C, subsequently cooled at a rate of 10 °C/min and crystallized at 104 °C. Magnification 120 times.

10           FIG. 2 is an optical photomicrograph of a film of isotactic polypropylene which contains 0.75 % by weight of the nucleating agent tris[3,4-bis(decyloxy)phenylene-carbonylimino-1,4-phenylene]amine, (hereinafter also referred to as compound I-1 of Table 1).  
15 The film was compression molded at 210 °C, subsequently cooled at a rate of 10 °C/min and crystallized at 104 °C. Magnification 120 times.

          FIG. 3 depicts Thermo-Gravimetric Analysis (TGA) records carried out under nitrogen on compounds I-5 (3)  
20 and I-7 (2) in Table 1 and Millad 3988 (1) showing the enhanced thermal stability of the compounds according to the present invention.

## The Nucleators

The nucleators for crystallizable thermoplastic polymers according to this invention are of the following general schematic formula:



5

wherein:

x is an integer from two to seven;

y is an integer from zero to four;

z is an integer from zero to four;

10 the sum  $x + y + z$  equals an integer from three to seven;

m is an integer from one to three.

In formula (1), A is a center that is covalently bonded to moieties B, B' or X', or combinations thereof, wherein the moieties B and B' comprise at least one unit capable of forming one or more intermolecular hydrogen bonds; and wherein the moieties X and X' are compatible with the crystallizable thermoplastic polymer, and wherein X is covalently bonded to B. The role of the center moiety A is to provide a means to connect a plurality of moieties B, B', or X' and combinations thereof that are beneficial for the formation of structures that induce nucleation of

the crystallizable thermoplastic polymer.

Preferred nucleators for crystallizable thermoplastic polymers according to this invention are  
5 those of the schematic formula (1), wherein:

x is an integer from three to six;  
y is an integer from zero to three;  
z is an integer from zero to two;  
the sum  $x + y + z$  equals an integer from three to  
10 seven;  
m is the integer one or two.

Among the preferred nucleators according to this invention more preferred are those of the formula (1)  
15 wherein:

x is the integer three or four;  
y is an integer from zero to two;  
z is the integer zero or one;  
the sum  $x + y + z$  equals an integer from three to six;  
20 m is the integer one or two.

Most preferred nucleators for crystallizable thermoplastic polymers according to this invention are of the general schematic formula (1), wherein:

25 x is three;  
y is an integer from zero to two;  
z is the integer zero or one;

the sum  $x + y + z$  equals an integer from three to six;  
m is the integer one or two.


Illustrative of moieties that are useful as the  
5 center A of the nucleators according to the present  
invention are carbon, nitrogen, phosphorus, boron and  
silicon, without and with one or more aromatic,  
cycloaliphatic, aliphatic, alkene, alkyne, diene, ether,  
thioether or ketone links, and combinations thereof,  
10 connected to them; unsubstituted and substituted, single  
and fused 4, 5, 6 or 7 membered aromatic and  
cycloaliphatic carbon rings, which rings may include one  
or more heteroatoms such as nitrogen, sulfur and oxygen,  
and combinations thereof, and without and with one or more  
15 aromatic, cycloaliphatic, aliphatic, alkene, alkyne,  
diene, ether, thioether or ketone links, and combinations  
thereof, connected to them.

Preferred moieties are carbon and nitrogen,  
20 without and with one or more aromatic, cycloaliphatic or -  
(CH<sub>2</sub>)<sub>p</sub>- links, and combinations thereof, connected to them,  
where p is 1 or 2; unsubstituted and substituted, single  
and fused 5 and 6 membered aromatic and cycloaliphatic  
carbon rings, which rings may include one or more  
25 heteroatoms such as nitrogen, sulfur or oxygen, and  
combinations thereof, and without and with one or more  
aromatic, cycloaliphatic or -(CH<sub>2</sub>)<sub>p</sub>- links, and

combinations thereof, connected to them, where p is 1 or 2.

Among the preferred moieties, more preferred  
5 moieties are carbon and nitrogen, with one or more  
aromatic or cycloaliphatic links, and combinations  
thereof, connected to them; unsubstituted and substituted,  
single and fused 6 membered aromatic and cycloaliphatic  
carbon rings, which rings may include one or more nitrogen  
10 atoms, without and with one or more aromatic,  
cycloaliphatic or  $-(CH_2)_p-$  links, and combinations thereof,  
connected to them, where p is 1 or 2.

Most preferred among the more preferred moieties  
15 that are useful as the center A of the nucleators  
according to the present invention are the following  
structures which may or may not be substituted:



The moieties B and B' of the nucleators according to the present invention are those moieties that are capable of forming one or more intermolecular hydrogen bonds between the nucleator molecules of which they are

part. Hereinafter, a hydrogen bond is defined as that bond that is due to the electrostatic interaction between a hydrogen atom and a strong electronegative element of small atomic radius, such as fluor, oxygen and nitrogen, and to a lesser extend, chlorine and sulfur (Lehrbuch der Organischen Chemie, H. Beyer; Hirzel, Stuttgart, 1976, p. 105, 106). The function of the moieties B and B' is to induce and guide and stabilize the formation of the structures that are beneficial for nucleation of the crystallizable thermoplastic polymer.

Illustrative examples of moieties B, which may be the same or different at each occurrence, are those that comprise esters, thioester, ethers, thioethers, ketones, secondary and tertiary amines, amides, imides, imines, azo, azoxy, ureas, urethanes, thiourethanes, sulfonamides and the like.














Preferred moieties B, which may be the same or different at each occurrence, are those that comprise one or more units selected among amides, imides, imines, ureas, urethanes, thiourethanes, sulfonamides and the like. Among the preferred moieties, more preferred moieties B, which may be the same or different at each occurrence, are those that comprise one or more units selected among amides, imides and sulfonamides. Especially preferred are those that comprise amide units.



Illustrative examples of moieties B', which may be the same or different at each occurrence, are those moieties that comprise acids such as carboxylic acids, sulfonic acids, alcohols, phenols, thiols, amines, acetamides, cyano groups, hydrazine, and the like.

The nucleators for crystallizable thermoplastic polymers according to the present invention comprise moieties X and X', the function of which is to compatibilize with, and assist in dispersing of the nucleators within the crystallizable thermoplastic polymers. Hence, selection of the particular chemical nature of the moieties X and X' is dependent on the choice of the crystallizable thermoplastic polymer. In general, nucleators comprising moieties X and X' that are of a polar nature are used in combination with the more polar thermoplastic polymers comprising polar groups. Nucleators comprising less polar moieties X and X' are used in combination with less polar thermoplastic polymers comprising few or no polar groups. Generally, the moieties X and X', which may or may not be chiral are the same or different at each occurrence and are selected from the group consisting of: H, linear and branched alkyl, alkenyl, alkoxy, alkanoyl, alkylthio, alkylthioalkyl, each having from 1 to about 20 carbon atoms; linear and branched alkylaryl, arylalkyl, alkylsulfinyl, alkoxyalkyl, alkylsulfonyl, alkoxycarbonyl, carboxylic acid, where the alkyl or alkoxy each has from 1 to about 20 carbon atoms;

alkyl having from 1 to about 20 carbon atoms substituted with one or more sulfonic acid, carboxylic acid, halogen, nitro, cyano, diazo, or epoxy moieties; one or more substituted and unsubstituted single and fused 3, 4, 5, 6 or 7 membered aromatic and alicyclic carbon rings, which rings may include one or more heteroatoms of nitrogen, sulfur, sulfinyl, sulfonyl or oxygen, such as thiophenyl, pyrrolyl, furanyl, pyridinyl, or combinations thereof.

10 The most preferred embodiments of this invention comprising nucleating agents are selected from the group consisting of:

Center: A	Substitution		
	B: - NH - CO -	m = 1	x = 3 y = 0 z = 0
	X': -	B': -	x + y + z = 3
	X: - CH <sub>2</sub> - CH <sub>2</sub> - CH <sub>2</sub> -		- CH <sub>2</sub> - 
			
			
			
			
	- C <sub>4</sub> H <sub>9</sub>	- C <sub>5</sub> H <sub>11</sub>	- C <sub>6</sub> H <sub>11</sub>



As an illustration of its use, and for further guidance, the above structures are also given according the notation of the schematic formula (1). Preferably, the above nucleators are used in combination with weakly, or non-  
5 polar, crystallizable thermoplastic polymers, such as isotactic polypropylene, and copolymers thereof.

The nucleators according to the present invention have thermal properties, such as melting temperatures, that may vary widely, depending on the  
10 precise structure of the nucleator. For use in the practice according to the present invention, the nucleators preferably have a solidification temperature, i.e. that temperature or temperature range in which the molten or dissolved nucleator forms an molecular aggregate  
15 or solid, is equal to, or exceeds the temperature at which the crystallizable thermoplastic polymer crystallizes in the absence of the nucleator of the present invention.

Particularly excluded from the present invention are those structures that are based on carbohydrates, or  
20 comprise carbohydrate units, such as, for example, sorbitol and its derivatives. Such structures generally are well-known, and suffer from limited thermal stability, and, hence, are of restricted use as nucleating agents or clarifiers, especially for crystallizable thermoplastic  
25 polymers that have high melting temperatures or softening points, which generally require high processing temperatures. By contrast, the compositions according to

the present invention have high decomposition temperatures, typically above 230 °C.

Some compounds of the general structural formula  
5 (1) have been described in the prior art. For example, Yasuda et al. described the preparation of N,N',N''-tristearyltrimidesamide (Chem. Letters, vol. 7, p. 575 (1996)). Also described is 4,4',4''-tris(stearoylamino)-triphenylamine (Y. Yasuda, Y. Takebe, M. Fukumoto, H.  
10 Inada and Y. Shirota, Adv. Mat., vol. 8, p. 740 (1996)). However, the use of such compounds in combination with crystallizable thermoplastic polymers, and, particularly, their use as nucleating agents for crystallizable thermoplastic polymers has not been disclosed or  
15 suggested.

The amount of the nucleator according to the present invention added to a crystallizable thermoplastic polymer is an "effective amount". As used herein, an  
20 "effective amount" is an amount which is sufficient to increase the crystallization peak temperature of the polymer by at least 3 °C. Such amounts will normally correspond to amounts of conventional nucleating agents. In the preferred embodiments of the present invention, the  
25 amount of the nucleator employed is in the range from about 0.005 weight percent to about 20 weight percent based on the total weight of the polymer in the composition, and in the particularly preferred embodiments

of this invention is from about 0.005 weight percent to about 10 weight percent, on the aforementioned basis. Amongst these particularly preferred embodiments, most preferred are those embodiments where the amount of nucleator employed is from about 0.005 weight percent to about 5 weight percent based on the total weight of the polymer in the composition according to the present invention.

The composition according to the present inventions are characterized in that the size of polymer spherulites in the thermoplastic polymer composition typically is less than 50 % of the size of spherulites in neat crystallized thermoplastic polymer that is void of the present nucleators; and, as a result, the former are of lower haze in comparison with the latter.

#### The Crystallizable Thermoplastic Polymers

The crystallizable thermoplastic polymers for use in the practice of this invention may vary widely, and are selected for the particular end uses of the product comprising the compositions of the present invention. Hence, the crystallizable thermoplastic polymers useful in the present invention include all thermoplastic polymers and copolymers commonly used in plastic products. Examples of useful crystallizable thermoplastic homopolymers or copolymers are polyolefins such as polyethylenes, stereoregular polypropylenes, ethylene-propylene copolymers, stereoregular polystyrenes, polynorbornene,

polyisobutylene, poly(1-butene), poly(3-methyl-1-butene),  
poly(1-pentene), poly(4-methyl-1-pentene), poly(1-hexene),  
poly(5-methyl-1-hexene), poly(2-methylstyrene), poly(4-  
methoxy styrene) and the like, and copolymers thereof,  
5 aromatic or aliphatic polyoxides such as polyoxymethylene,  
poly(ethylene oxide), poly(tetra-methyloxide), poly-  
(propylene oxide), polyphenylene oxides, polysulfides such  
as poly(propylene sulfide), poly(phenylene sulfide) and  
the like, and copolymers thereof, aromatic, aliphatic and  
10 aromatic-aliphatic polyamides, such as nylon 6, nylon 12,  
nylon 6.6, nylon 6.10, and the like, aromatic, aliphatic  
and aromatic-aliphatic polyesters, such as poly(ethylene  
terephthalate), poly(butylenterephthalate), poly-  
(ethyleneterephthalate), poly(vinylalcohol), polycarbonates.

15

In addition to the above essential components,  
the compositions according to the present invention may  
optionally include one or more other components which are  
additives commonly employed with thermoplastic resins.  
20 Such optional components include fillers, reinforcing  
components, plasticizers, dispersion aids, impact  
modifiers, chain extenders, colorants, mold release  
agents, metal deactivators, antioxidants, light  
stabilizers, lubricants, antistatic agents, fire  
25 retardants, fluorescent whitening agents, biostabilizers,  
chemical blowing agents, cross-linking agents and other  
nucleating agents. These optional components are well  
known to those skilled in the art, and are described in

standard texts and handbooks such as Plastics Additives Handbook (4th Ed. Hanser, Munich, 1990).

5       The compositions according to the present invention can be prepared by blending or mixing the essential ingredients, and other optional components as uniformly as possible employing conventional compounding means. Appropriate compounding means, such as extrusion, batch blending and the like, are well known in the art and  
10 will not be described here in detail. Also, all or a portion of the various components can be masterbatched or preblended in the melt or in an appropriately selected solvent.

15       The compositions according to the present invention are outstandingly suitable for the production of films, fibers, containers, coatings, parts, membranes, rods, tubes, fabrics, and foams and the like that are of improved clarity and mechanical properties, and that are  
20 manufactured at reduced cycling times. Thus, the present invention further relates to a process for enhancing the rate of crystallization of a crystallizable thermoplastic polymer that comprises the addition of an amount between about 0.001 percent by weight and about 20 percent by  
25 weight of one or more nucleators to yield the above shaped objects.

In specific embodiments, the composition of the present invention comprises the following combinations: one or more polyolefins, such as polyethylenes, stereoregular polypropylenes and ethylene-propylene  
5 copolymers and one or more of the following nucleators of formula (1), wherein:

- i) the center A is a single atom selected from the group consisting of nitrogen and phosphorus; or A is an unsubstituted or substituted, single or fused 5 or 6  
10 membered heterocyclic aromatic or nonaromatic ring, which ring includes carbon and one or more atoms such as nitrogen, sulfur or oxygen, or combinations thereof; and
- ii) moieties B that are the same at each occurrence and comprise amides or ureas; or moieties B that are not the  
15 same at each occurrence and comprise at least 2 amides and at least 1 moiety selected from the group consisting of esters and ureas; or moieties B that are not the same at each occurrence and that comprise at least 2 ureas and at least 1 moiety selected from the group consisting of  
20 esters and amides.

iii) x is three; y is the integer zero or one; z is the integer zero or one; m is the integer one or two.

## EXAMPLES

The compounds of the formula (1) can be prepared by methods known per se, as described in the literature (for example in the standard works such as Houben-Weyl, Methoden der Organischen Chemie [Methods of Organic Chemistry], published by Georg Thieme, Stuttgart), under reaction conditions which are known. In carrying out these reactions, it is also possible to take advantage of variants known per se which are not specifically mentioned here. The starting substances can, if so desired also be formed in situ, by not isolating them out of the reaction mixture but immediately reacting them further to the compounds of the formula (1).

The compounds related to the invention are illustrated by the examples which follow. Given are m.p. = melting points of the various compounds. Heretofore and hereinafter, percentages are by weight; all temperatures are given in degrees Celsius, °C. "Customary working up" means: addition to water, filtration of precipitate, extracting with organic solvent and/or purifying the product by crystallization and/or chromatography.

## Example A:

4.05 g (10.2 mmol) 3,4-bis(octyloxy)benzoic acid chloride and 0.5 g dry LiCl were added under inert atmosphere to 50 ml of dry NMP and 5 ml of dry pyridine and cooled to 5 °C. 0.99 g (3.4 mmol) tris(4-aminophenylene)amine was added. The reaction mixture was

heated to 75 °C. After 2 hours the reaction mixture was added to 500 ml of distilled water. The precipitate was filtered off. Customary work-up gives tris[3,4-bis(octyloxy)phenylene-carbonylimino-1,4-phenylene]amine

5 (Table I, No. I-7). m.p.: 229 °C.

The following compounds were prepared analogously:

tris[3,4-bis(decyloxy)phenylene-carbonylimino-1,4-phenylene]amine (compound I-1), m.p.: 211 °C;

10 tris[3,4-bis(nonyloxy)phenylene-carbonylimino-1,4-phenylene]amine (compound I-2), m.p.: 219 °C;

tris[3,4,5-tris(ethyloxy)phenylene-carbonylimino-1,4-phenylene]amine (compound I-3), m.p.: 258 °C;

15 tris[cyclopentyl-carbonylimino-1,4-phenylene]amine (compound I-4), m.p.: 270 °C;

tris[cyclohexyl-carbonylimino-1,4-phenylene]amine (compound I-5), m.p.: 276 °C;

tris[3-cyclohexylpropylene-carbonylimino-1,4-phenylene]amine (compound I-6), m.p.: 238 °C;

20 tris[cyclohexylmethylenecarbonylimino-1,4-phenylene]amine (compound I-8), m.p.: 335 °C;

tris[phenylcarbonylimino-1,4-phenylene]amine (compound I-9), m.p.: 198 °C.

25 Example B:

1.76 g (12.0 mmol) cyclohexanecarboxylic acid chloride and 0.5 g dry LiCl were added under inert atmosphere to 50 ml of dry NMP and 5 ml of dry pyridine

and cooled to 5 °C. 0.40 g (3.0 mmol) 2,4,6-triaminotoluene was added. The reaction mixture was heated to 75 °C. After 2 hours the reaction mixture was added to 500 ml of distilled water. The precipitate was filtered off.  
5 Customary work-up gives 2,4,6-(cyclohexanecarbonylimino)-toluene (Table I, No. II-1). m.p.: 199 °C.

Example C:

1.75 g (10.0 mmol) 4-cyclohexylphenylamine and  
10 0.5 g dry LiCl were added under inert atmosphere to 50 ml of dry NMP and 5 ml of dry pyridine and cooled to 5 °C. 0.80 g (3.0 mmol) 1,3,5-benzenetricarboxylic acid chloride was added. The reaction mixture was heated to 75 °C. After 2 hours the reaction mixture was added to 500 ml of  
15 distilled water. The precipitate was filtered off. Customary work-up gives 1,3,5-(cyclohexyl-1,4-phenyleneiminocarbonyl)benzene (Table I, No. III-2). m.p.: 317 °C.

The following compounds were prepared  
20 analogously:

1,3,5-(4-t-butylphenyleneiminocarbonyl)benzene  
(compound III-1), m.p.: 358 °C;  
1,3,5-(4-hexyloxyphenyleneiminocarbonyl)benzene  
(compound III-3), m.p.: 80 °C;  
25 1,3,5-(n-butyliminocarbonyl)benzene  
(compound III-4), m.p.: 219 °C;  
1,3,5-(phenyliminocarbonyl)benzene  
(compound III-5), m.p.: 311 °C.

## Example D:

3.00 g (10.3 mmol) tris(4-aminophenylene)amine and 0.1 g dry LiCl were added under inert atmosphere to 70 ml of dry NMP and 10 ml of dry pyridine and cooled to 5 °C. 4.30 g (36.2 mmol) phenylisocyanate was added. The reaction mixture was heated to 75 °C. After 2 hours the reaction mixture was added to 400 ml of cold distilled water. The precipitate was filtered off. Customary work-up gives tris[phenyliminocarbonylimino-1,4-phenylene]amine- (Table I, No. IV-1). m.p.: 278 °C.

The following compound was prepared analogously: tris[cyclohexyliminocarbonylimino-1,4-phenylene]amine (compound IV-2). m.p.: 230 °C.

## 15 Example E:

1.89 g (15.0 mmol) 2,4,6-triamino-1,3,5-triazine and 35 ml triethylamine were added under inert atmosphere to 130 ml of dry 1,4-dioxane and cooled to 5 °C. 9.28 g (60.0 mmol) 3-methylbenzoic acid chloride was added. The reaction mixture was heated under reflux for 3 hours. The reaction mixture was cooled to room temperature and added to 600 ml of cold distilled water. The precipitate was filtered off, dried. Customary work-up gives tris[3-methylphenylenecarbonylimino]-1,3,5-triazine. (Table I, No. V-1). m.p.: 227 °C.

The following compound was prepared analogously: tris[phenylcarbonylimino]-1,3,5-triazine (compound V-2). m.p.: 277 °C.

## Example F:

1.89 g (15.0 mmol) 2,4-diamino-6-hydroxypyrimidine and 0.1 g dry LiCl were added under inert atmosphere to 130 ml of dry NMP and 25 ml of dry  
5 pyridine and cooled to 5 °C. 8.06 g (55.0 mmol) cyclohexanecarboxylic acid chloride was added. The reaction mixture was heated to 75 °C. After 2 hours the reaction mixture was added to 400 ml of cold distilled water. The precipitate was filtered off. Customary work-up  
10 gives 2,4-bis[cyclohexylcarbonylimino], 6-[cyclohexylcarbonyloxy]pyrimidine. (Table I, No. VI). m.p.: 225 °C.

## Example G:

15 1.40 g (5.8 mmol) 3,5-diaminobenzoic acid-4-methylphenyl ester was added under inert atmosphere to 30 ml of dry NMP and 1.3 ml of dry pyridine and cooled to 5 °C. 2.16 g (14.0 mmol) phenylacetyl chloride was added. The reaction mixture was heated to 90 °C. After 2 hours  
20 the reaction mixture was added to 400 ml of cold distilled water. The precipitate was filtered off. Customary work-up gives 3,5-bis[benzylcarbonylimino]benzoic acid-4-methylphenyl ester. (Table I, No. VII). m.p.: 212 °C.

## 25 Example H:

1.5 g (9.8 mmol) 3,5-diaminobenzoic acid-3,5-dimethyl-phenylamide was added under inert atmosphere to 30 ml of dry NMP and cooled to 5 °C. 2.70 g (21.6 mmol)

cyclohexyl isocyanate was added. The reaction mixture was heated to 75 °C. After 4.5 hours the reaction mixture was added to 300 ml of cold distilled water. The precipitate was filtered off. Customary work-up gives 3,5-  
5 bis[cyclohexyliminocarbonylimino]benzoic acid-3,5-dimethylphenyl-amide. (Table I, No. VIII). m.p.: 295 °C.

## I. GENERAL PROCEDURES

### 10 A. Mixing Procedure A

About 20 mg (1 % by weight) of the powdered additive was added to about 2 g of the powdered isotactic polypropylene and refluxed in a flask with 100 ml of p-xylene (Aldrich Chemical Co.) at 120 °C for about 1 hr.  
15 Subsequently, the flask was cooled to room temperature. The mixture was then further cooled with liquid nitrogen and freeze-dried at room temperature under vacuum, yielding a powdered polypropylene-additive mixture. The neat polypropylene was also treated similarly to obtain a  
20 reference control sample.

### B. Mixing Procedure B-1

About 50 mg (1 % by weight) of powdered additive was added to about 4.95 g of the powdered isotactic  
25 polypropylene (Aldrich Chemical Co.), tumble mixed and ground in a mortar. Portions of this mixture were heated to 220 °C, unless indicated otherwise, for a period of about 5 to 10 min, and subsequently cooled down to room

temperature. Polypropylene alone was similarly treated to produce a blank control sample. The loading of the additives was 1 % by weight unless otherwise noted.

5 B. Mixing Procedure B-2

To 59.91 g of the powdered isotactic polypropylene (Aldrich Chemical Co.) or to a copolymer of isotactic polypropylene comprising a minor amount of ethylene comonomer (ELF-Atochem) 90 mg of powdered  
10 additive (0.15 % by weight) was added, and tumble-mixed for 24 h in a glass container. Portions of this mixture were compounded at 230 °C in a small-scale, laboratory twin-screw, recycling extruder for a period of about 10 min, and subsequently collected at room temperature. The  
15 polypropylenes alone were similarly treated to produce a blank control sample.

C. Differential Scanning Calorimetry (DSC)

A Perkin-Elmer DSC instrument (Model DSC 7),  
20 operated in a dry nitrogen atmosphere, was used for the analysis of the crystallization behavior of the various mixtures and control samples, according to standard procedures. About 5 to 10 mg of sample was sealed into an aluminium cup, heated from 130 °C to 230 °C at a rate of 10  
25 °C/min, held at 220 °C for 5 min, and then subsequently cooled at a rate of 10 °C/min to 50 °C. The data represented as crystallization peak temperatures ( $T_C$ ) are

the peak temperatures of the exotherms in the thermograms that were recorded upon cooling.

#### D. Thermo-Gravimetric Analysis (TGA)

5           An automated Netzsch TGA instrument (STA 409) operated in nitrogen was used for the analysis of the thermal stability of selected samples. About 10 mg of sample was placed into an aluminum oxide crucible and heated from 50 °C to 640 °C at a rate of 10 °C/min.

#### E. Optical Microscopy

10           Selected samples were produced by forming a film from the melt by compression molding at 210 °C and subsequent cooling at a rate of 10 °C/min. These samples  
15           were examined in a polarizing optical microscope (Leitz Laborlux 12-Pol) under crossed Nicols in transmitted light.

## 20   II. DESCRIPTION OF EXAMPLES

### Example 1.

          Tris[3,4-bis(decyloxy)phenylene-carbonylimino-  
1,4-phenylene]amine, (compound I-1 in Table 1) (1 % by  
weight) was mixed with polypropylene, using the mixing  
25           procedure A. Both the neat polypropylene reference sample and the mixture were analyzed by Differential Scanning Calorimetry. The crystallization peak temperature of the

mixture is 12.4 °C higher than that of the neat control sample.

In the following, this difference between the crystallization temperatures of a mixture according to the present invention and that of the control sample is designated  $\Delta T$ , which equals 12.4 °C in the present example.

#### Example 2.

Compound I-6 in Table 1 (1 % by weight) was mixed with polypropylene, using the mixing procedure B. Both the neat polypropylene reference sample and the mixture were analyzed by Differential Scanning Calorimetry.  $\Delta T = 13.0$  °C.

#### Example 3.

Examples 1 and 2 were repeated with various compounds that were mixed with polypropylene, using either mixing method A (compounds I-1 and I-2) or method B (B1: compounds I-3, I-6, I-8, I-9, II-1, III-1, III-2, III-3, III-4 and III-5; B2: compounds I-4, I-5, I-7, IV-1, IV-2, V-1, V-2, VI, VII and VIII). The following Table 1 collects results that were measured using DSC.

Table I:











No.	Center: A	Substitution	$\Delta T [^{\circ}\text{C}]$
	polypropylene reference	none	0,0
I-1		<p>B: <math>-\text{NH}-\text{CO}-</math> <math>m = 1</math></p> <p>X:  <math>x = 3</math>  <math>y = 0</math>  <math>z = 0</math></p> <p>X': - B': - <math>x + y + z = 3</math></p>	12,4
I-2		<p>B: <math>-\text{NH}-\text{CO}-</math> <math>m = 1</math></p> <p>X:  <math>x = 3</math>  <math>y = 0</math>  <math>z = 0</math></p> <p>X': - B': - <math>x + y + z = 3</math></p>	12,2
I-3		<p>B: <math>-\text{NH}-\text{CO}-</math> <math>m = 1</math></p> <p>X:  <math>x = 3</math>  <math>y = 0</math>  <math>z = 0</math></p> <p>X': - B': - <math>x + y + z = 3</math></p>	6,6
I-4		<p>B: <math>-\text{NH}-\text{CO}-</math> <math>m = 1</math></p> <p>X:  <math>x = 3</math>  <math>y = 0</math>  <math>z = 0</math></p> <p>X': - B': - <math>x + y + z = 3</math></p>	17,0
I-5		<p>B: <math>-\text{NH}-\text{CO}-</math> <math>m = 1</math></p> <p>X:  <math>x = 3</math>  <math>y = 0</math>  <math>z = 0</math></p> <p>X': - B': - <math>x + y + z = 3</math></p>	19,0

Table I (continued):











No.	Center: A	Substitution	$\Delta T [^{\circ}\text{C}]$
I-6		B: $-\text{NH}-\text{CO}-$ <span style="float: right;"><math>m = 1</math></span> $x = 3$ X: $-\text{CH}_2-\text{CH}_2-\text{CH}_2-$  <span style="float: right;"><math>y = 0</math></span> $z = 0$ $x + y + z = 3$	13,0
I-7		B: $-\text{NH}-\text{CO}-$ <span style="float: right;"><math>m = 1</math></span> $x = 3$ X: $-\text{CH}_2-$  <span style="float: right;"><math>y = 0</math></span> $z = 0$ $x + y + z = 3$	15,0
I-8		B: $-\text{NH}-\text{CO}$ <span style="float: right;"><math>m = 1</math></span> $x = 3$ X: $-\text{CH}_2-$  <span style="float: right;"><math>y = 0</math></span> $z = 0$ $x + y + z = 3$	15,4
I-9		B: $-\text{NH}-\text{CO}-$ <span style="float: right;"><math>m = 1</math></span> $x = 3$ X:  <span style="float: right;"><math>y = 0</math></span> $z = 0$ $x + y + z = 3$	14,3
II-1		B: $-\text{NH}-\text{CO}-$ <span style="float: right;"><math>m = 1</math></span> $x = 3$ X:  <span style="float: right;"><math>y = 0</math></span> $z = 0$ $x + y + z = 3$	7,1

Table I (continued):










No.	Center: A	Substitution	$\Delta T [^{\circ}\text{C}]$
III - 1		B: $-\text{CO}-\text{NH}-$	$m = 1$
		X: 	$x = 3$
			$y = 0$
			$z = 0$
		X': -      B': -	$x + y + z = 3$
III - 2		B: $-\text{CO}-\text{NH}-$	$m = 1$
		X: 	$x = 3$
			$y = 0$
			$z = 0$
		X': -      B': -	$x + y + z = 3$
III - 3		B: $-\text{CO}-\text{NH}-$	$m = 1$
		X: 	$x = 3$
			$y = 0$
			$z = 0$
		X': -      B': -	$x + y + z = 3$
III - 4		B: $-\text{CO}-\text{NH}-$	$m = 1$
		X: $-\text{C}_4\text{H}_9$	$x = 3$
			$y = 0$
			$z = 0$
		X': -      B': -	$x + y + z = 3$
III - 5		B: $-\text{CO}-\text{NH}-$	$m = 1$
		X: 	$x = 3$
			$y = 0$
			$z = 0$
		X': -      B': -	$x + y + z = 3$

Table I (continued):











No.	Center: A	Substitution	$\Delta T [^{\circ}\text{C}]$
IV - 1		B: $-\text{NH}-\text{CO}-\text{NH}-$	$m = 1$
		X: 	$x = 3$
		X': -    B': -	$y = 0$ $z = 0$ $x + y + z = 3$
IV - 2		B: $-\text{NH}-\text{CO}-\text{NH}-$	$m = 1$
		X: 	$x = 3$
		X': -    B': -	$y = 0$ $z = 0$ $x + y + z = 3$
V - 1		B: $-\text{NH}-\text{CO}-$	$m = 1$
		X: 	$x = 3$
		X': -    B': -	$y = 0$ $z = 0$ $x + y + z = 3$
V - 2		B: $-\text{NH}-\text{CO}-$	$m = 1$
		X: 	$x = 3$
		X': -    B': -	$y = 0$ $z = 0$ $x + y + z = 3$
VI		B: $2x \text{ } -\text{NH}-\text{CO}-$ $1x \text{ } -\text{O}-\text{CO}-$	$m = 1$
		X: 	$x = 3$
		X': -    B': -	$y = 0$ $z = 0$ $x + y + z = 3$

Table I (continued):











No.	Center: A	Substitution	$\Delta T [^{\circ}\text{C}]$
VII		B: $2x \text{ } -\text{NH}-\text{CO}-$	$m = 1$
		$1x \text{ } -\text{CO}-\text{O}-$	
		X: $2x \text{ } -\text{CH}_2-$ 	$x = 3$
		$1x \text{ } -$ 	$y = 0$
		X': - B': - $x + y + z = 3$	$z = 0$ 4,1
VIII		B: $2x \text{ } -\text{NH}-\text{CO}-\text{NH}-$	$m = 1$
		$1x \text{ } -\text{CO}-\text{NH}-$	
		X: $2x \text{ } -$ 	$x = 3$
		$1x \text{ } -$ 	$y = 0$
		X': - B': - $x + y + z = 3$	$z = 0$ 3,5

Table II:

No.	Center: A	Substitution	$\Delta T [^{\circ}\text{C}]$
polypropylene/ethylene copolymer reference		none	0,0
I - 4		B: $-\text{NH}-\text{CO}-$	$m = 1$
		X: 	$x = 3$
			$y = 0$
			$z = 0$
		X': - B': - $x + y + z = 3$	11,8
I - 5		B: $-\text{NH}-\text{CO}-$	$m = 1$
		X: 	$x = 3$
			$y = 0$
			$z = 0$
		X': - B': - $x + y + z = 3$	12,5

## Example 4.

Films of neat, nucleator-free polypropylene and polypropylene containing 1 % by weight of tris[3,4-bis(decyloxy)phenylene-carbonylimino-1,4-phenylene]amine, (compound I-1 in Table 1) were compression molded at 210 °C, subsequently cooled at a rate of 10 °C/min and crystallized at 104 °C. FIG. 1 is an optical photomicrograph of polypropylene which does not contain a nucleating agent. FIG. 2 is an optical photomicrograph of isotactic polypropylene which contains 1 % by weight of compound I-1. A comparison between the two photomicrographs, which were taken at the same magnification, shows that the spherulite size is much less than 50 % for the polypropylene film which contains the additive than for the neat reference polypropylene, which is indicative of the nucleating ability of the additive; and is the origin of the reduced haze of the former.


## Example 5.

Thermo-Gravimetric Analysis (TGA) was carried out under nitrogen on compounds I-5 (curve 3) and I-7 (curve 2) in Table 1 and Millad 3988 (curve 1). FIG. 3 depicts their respective TGA-curves showing the enhanced thermal stability of the compounds according to the present invention.

What is claimed is:

1. A composition comprising (i) a crystallizable thermoplastic polymer and (ii) one or more nucleators of the formula

5



wherein:

x is an integer from two to seven;

y is an integer from zero to four;

10 z is an integer from zero to four;

the sum  $x + y + z$  equals an integer from three to seven;

m is an integer from one to three;

and wherein A is a center that is covalently bonded with  
 15 moieties B, B' or X', or combinations thereof; wherein  
 said moieties B and B' comprise at least one unit capable  
 of forming one or more intermolecular hydrogen bonds;  
 wherein moieties X and X' are compatible with said  
 crystallizable thermoplastic polymer; and wherein X is  
 20 covalently bonded to B.

2. A composition according to claim 1 wherein  
 said center A is selected from the group consisting of  
 carbon, nitrogen, phosphorus, boron and silicon, which may

be substituted with one or more aromatic, cycloaliphatic, aliphatic, alkene, alkyne, diene, ether, thioether or ketone links, and combinations thereof, connected to them; unsubstituted and substituted, single and fused 4, 5, 6 or 5 7 membered aromatic and cycloaliphatic carbon rings, which rings may include one or more heteroatoms such as nitrogen, sulfur and oxygen, and combinations thereof, which may be substituted with one or more aromatic, cycloaliphatic, aliphatic, alkene, alkyne, diene, ether, 10 thioether or ketone links, and combinations thereof.

3. A composition according to claims 1 or 2 wherein said moiety B, which may be the same or different at each occurrence, comprises one or more units selected 15 from the group consisting of esters, thioester, ethers, thioethers, ketones, secondary and tertiary amines, amides, imides, imines, azo, azoxy, ureas, urethanes, thiourethanes and sulfonamides.

20 4. A composition according to any of claims 1 to 3 wherein said moiety B', which may be the same or different at each occurrence, are selected from the group of moieties that comprises one or more carboxylic acid and sulfonic acid, alcohol, phenol, thiol, amine, acetamide, 25 cyano and hydrazine groups.

5. A composition according to any of claims 1 to 4 wherein said moieties X and X', which may or may not be

chiral, and are the same or different at each occurrence are selected from the group consisting of: H, linear and branched alkyl, alkenyl, alkoxy, alkanoyl, alkylthio, alkylthioalkyl, each having from 1 to 20 carbon atoms; 5 linear and branched alkylaryl, arylalkyl, alkylsulfinyl, alkoxyalkyl, alkylsulfonyl, alkoxycarbonyl, carboxylic acid, where the alkyl or alkoxy each has from 1 to 20 carbon atoms; alkyl having from 1 to 20 carbon atoms substituted with one or more sulfonic acid, carboxylic 10 acid, halogen, nitro, cyano, diazo, or epoxy moieties; one or more substituted and unsubstituted single and fused 3, 4, 5, 6 or 7 membered aromatic and alicyclic carbon rings, which rings may include one or more heteroatoms of nitrogen, sulfur, sulfinyl, sulfonyl or oxygen or 15 combinations thereof.


6. A composition according to any of claims 1 to 5, wherein said composition is characterized in that its peak temperature of crystallization is at least 3 ° C 20 higher than the peak temperature of crystallization of said crystallizable thermoplastic polymer.

7. A composition according to any of claims 1 to 6, wherein said composition is characterized in that the 25 size of polymer spherulites in said composition is less than 50 % of the size of spherulites in neat crystallized thermoplastic polymer that is void of said nucleators.

8. A process for enhancing the rate of crystallization of a crystallizable thermoplastic polymer that comprises the addition of an amount between about 0.001 percent by weight and about 20 percent by weight of one or more nucleators as defined in any of claims 1 to 6.

9. Shaped objects comprising the composition according to any of claims 1 to 7 selected from the group consisting of films, fibers, containers, coatings, parts, membranes, rods, tubes, fabrics, and foams.

10. A compound of the general formula



wherein A, B, B', X, X', m, x, y, and z are defined in claim 1; wherein A is substituted or unsubstituted triphenylamine; wherein B comprises an amide unit; and wherein y and z equal zero, under the proviso that the compound 4,4',4''-tris(stearoylamino)triphenylamine is excluded.

11. Use of a compound of formula (1) as defined in any of claims 1 to 5 as a nucleating agent for a crystallizable thermoplastic polymer.

12. A thermoplastic polymer composition comprising:


a) one or more polyolefins selected from the group consisting of polyethylenes, stereoregular polypropylenes  
5 and ethylene-propylene copolymers; and

b) one or more of the nucleators according to formula (1), wherein:

i) the center A is a single atom selected from the group consisting of nitrogen and phosphorus; or A is an  
10 unsubstituted or substituted, single or fused 5 or 6 membered heterocyclic aromatic or nonaromatic ring, which ring includes carbon and one or more atoms such as nitrogen, sulfur or oxygen, or combinations thereof; and  
ii) moieties B that are the same at each occurrence and  
15 comprise amides or ureas; or moieties B that are not the same at each occurrence and comprise at least 2 amides and at least 1 moiety selected from the group consisting of esters and ureas; or moieties B that are not the same at each occurrence and that comprise at least 2 ureas and at  
20 least 1 moiety selected from the group consisting of esters and amides.


iii) x is three; y is the integer zero or one; z is the integer zero or one; m is the integer one or two.

Figure 1




Best Available Copy

Figure 2



Best Available Copy

Figure 3



# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP 99/01429

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 6 C08K5/00 C08K5/12 C08K5/20 C07C69/017		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC 6 C08K C07C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 780 428 A (MITSUI TOATSU CHEMICALS) 25 June 1997 (1997-06-25)	1-3,5,8, 9,11
Y	page 9, line 35; claim 1  ---	1-4,8,9, 11
Y	JP 60 252655 A (MITSUBISHI YUKA KK) 13 December 1985 (1985-12-13) the whole document  ---  -/-	1-4,8,9, 11
<div style="display: flex; justify-content: space-between;"> <span><input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.</span> <span><input checked="" type="checkbox"/> Patent family members are listed in annex.</span> </div>		
<div style="display: flex;"> <div style="flex: 1;"> <p>* Special categories of cited documents :</p> <p>*A* document defining the general state of the art which is not considered to be of particular relevance</p> <p>*E* earlier document but published on or after the international filing date</p> <p>*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>*O* document referring to an oral disclosure, use, exhibition or other means</p> <p>*P* document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="flex: 1;"> <p>*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>*Z* document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search  <div style="text-align: center; font-size: 1.2em;">7 October 1999</div>		Date of mailing of the international search report  <div style="text-align: center; font-size: 1.2em;">12.2.10.99</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer  <div style="text-align: center; font-size: 1.2em;">Devriese, K</div>

# INTERNATIONAL SEARCH REPORT

Int. lional Application No  
PCT/EP 99/01429

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	CHEMICAL ABSTRACTS, vol. 125, no. 24, 9 December 1996 (1996-12-09) Columbus, Ohio, US; abstract no. 309830, XP002073173 abstract	1-4,8,9, 11
Y	& YASUDA, Y. ET AL.: "4,4',4''," ADV.MATER., vol. 8, no. 9, 1996, pages 740-741,	1-4,8,9, 11
X	---	10
Y	DATABASE BEILSTEIN [Online] Ref. 1646400, Comp. Reg. No. 1989871, XP002073174 & JOURNAL ISOSHIMA, NPKZAZ, NIPPON KAGAKU ZASSHI, 77, 1956, 422, 431 abstract	1-4,8,9, 11
Y	---	
Y	DATABASE BEILSTEIN [Online] Ref. 279234, comp. Reg. No. 2030045, XP002073175 & Alekseeva, L.A. et al., J. ORG. CHEM. USSR (ENGL. TRANSL.), 10, 1974, 1063-1068 abstract	1-4,8,9, 11
Y	---	
Y	DATABASE BEILSTEIN [Online] Ref. 1985261, Comp. Reg. No. 2489023, XP002073176 & Rosenmund, Lohfert, Chem. Ber. 61, 1928, 2607 abstract	1-4,8,9, 11
Y	---	
Y	DATABASE BEILSTEIN [Online] Ref. 2029913, Comp. Reg. No. 3455889, XP002073177 & David, Imer, Bull. Soc. Chim. Fr., 1953, 183 abstract	1-4,8,9, 11
Y	---	
Y	DATABASE BEILSTEIN [Online] Ref. 5818304, Comp. Reg. No. 6557393 and 6558299, XP002073178 & Takenada et al. Mol. Cryst. Liq. Cryst, 111, 1984, 227-236 abstract	1-4,8,9, 11
Y	---	
Y	DATABASE BEILSTEIN [Online] Ref. 5881807, Comp. Reg. No. 6885534 and 6886402, XP002073179 & AKOPOVA, ET AL. J. GEN. CHEM. USSR (ENGL) 57, 1987, 570-574 abstract	1-4,8,9, 11
	---	
	-/--	

# INTERNATIONAL SEARCH REPORT

Int. ional Application No  
PCT/EP 99/01429

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>DATABASE BEILSTEIN [Online] REF. 6046315, COMP. REG. NO. 7649924, XP002073180 &amp;pARMAR ET AL. BIOORG.MED.CHEM.LETT,6,19,1996,2269-2274 abstract</p>	1-4,8,9, 11
Y	<p>--- US 4 294 747 A (SU TIEN-KUEI) 13 October 1981 (1981-10-13) cited in the application</p>	1-4,8,9, 11
X	<p>column 2, line 29-60; claim 1</p>	1,11
Y	<p>--- US 5 278 216 A (ASANUMA TADASHI ET AL) 11 January 1994 (1994-01-11) cited in the application</p>	1-4,8,9, 11
X	<p>column 4, line 21-41; claim 1</p>	1,11
Y	<p>--- US 3 367 926 A (VOEKS JOHN F) 6 February 1968 (1968-02-06) cited in the application claim 1; tables 2-8</p>	1-4,8,9, 11
X	<p>--- EP 0 278 409 A (IDEMITSU PETROCHEMICAL CO) 17 August 1988 (1988-08-17) page 4, line 40-50; claim 1</p>	1-12
X	<p>--- GB 2 310 860 A (EASTMAN KODAK CO) 10 September 1997 (1997-09-10) page 8, line 1 -page 9, line 40; claim 1 -----</p>	1-7,9,12

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/EP 99/01429

### Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

### Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☒ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:  
1-9,11 with A=C and B=ester-group;1-12 with A=N
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-9,11 (partially)

Searched:

I.1 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an ester-group

2. Claims: 1-9,11

Not searched

I.2 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a thioester-group

3. Claims: 1-9,11

Not searched

I.3 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an ether-group

4. Claims: 1-9,11

Not searched

I.4 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a thioether-group

5. Claims: 1-9,11

Not searched

I.5 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a ketone-group

6. Claims: 1-9,11

Not searched

I.6 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a prim. or sec. amine-group

7. Claims: 1-9,11

Not searched

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

I.7 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an amide group

8. Claims: 1-9,11

Not searched

I.8 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an imide group

9. Claims: 1-9,11

Not searched

I.9 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an imine-group

10. Claims: 1-9,11

Not searched

I.10 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an azo-group

11. Claims: 1-9,11

Not searched

I.11 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is an urea-group

12. Claims: 1-9,11

Not searched

I.12 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a urethane group

13. Claims: 1-9,11

Not searched

I.13 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a thiourethane group

14. Claims: 1-9,11

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Not searched

I.14 Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is carbon and B is a sulfonamide-group

15. Claims: 1-11, 12

Not searched

II Claims 1-9,11,12 with respect to compounds according to formula 1 with respect to A is nitrogen and claim 10.

16. Claims: 1-9,11,12

Not searched

III Claims 1-9,11,12 with respect to compounds according to formula 1 with respect to A is phosphorous

17. Claims: 1-9,11

Not searched

IV Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is boron

18. Claims: 1-9,11

Not searched

V Claims 1-9,11 with respect to compounds according to formula 1 with respect to A is silicon

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int .ional Application No

PCT/EP 99/01429

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0780428 A	25-06-1997	JP 9278991 A	28-10-1997
JP 60252655 A	13-12-1985	NONE	
US 4294747 A	13-10-1981	AT 380262 B	12-05-1986
		AT 474480 A	15-09-1985
		AU 533775 B	08-12-1983
		AU 6257280 A	09-04-1981
		CH 645910 A	31-10-1984
		DE 3035682 A	09-04-1981
		DK 401080 A	25-03-1981
		FR 2465762 A	27-03-1981
		GB 2061290 A,B	13-05-1981
		IE 50315 B	02-04-1986
		IT 1128566 B	28-05-1986
		LU 82796 A	04-06-1981
		NL 8005331 A,B,	26-03-1981
		NZ 195047 A	23-11-1982
		BE 885341 A	23-03-1981
		CA 1153845 A	13-09-1983
		JP 1395715 C	24-08-1987
		JP 56103242 A	18-08-1981
		JP 61056253 B	01-12-1986
US 5278216 A	11-01-1994	CA 2030532 A,C	19-10-1990
		DE 69024442 D	08-02-1996
		DE 69024442 T	01-08-1996
		EP 0419677 A	03-04-1991
		ES 2081368 T	01-03-1996
		WO 9012843 A	01-11-1990
		KR 9404846 B	02-06-1994
		AU 622538 B	09-04-1992
		AU 5358590 A	05-11-1990
		AU 5433090 A	16-11-1990
		CA 2030807 C	12-09-1995
		CA 2030807 A	12-10-1990
		DE 69017206 D	30-03-1995
		DE 69017206 T	12-10-1995
		EP 0466926 A	22-01-1992
		ES 2070319 T	01-06-1995
		WO 9012057 A	18-10-1990
		WO 9012839 A	01-11-1990
		KR 9310654 B	05-11-1993
		US 5232992 A	03-08-1993
		JP 3054238 A	08-03-1991
US 3367926 A	06-02-1968	NONE	
EP 0278409 A	17-08-1988	JP 8026192 B	13-03-1996
		JP 63193944 A	11-08-1988
		JP 1090238 A	06-04-1989
		JP 2118293 C	06-12-1996
		JP 8013911 B	14-02-1996
		CA 1318425 A	25-05-1993
		DE 3884002 D	21-10-1993
		DE 3884002 T	21-04-1994
		US 5030682 A	09-07-1991

Information on patent family members

PCT/EP 99/01429

Patent document  
cited in search report

Publication  
date

Patent family member(s)

Publication  
date

GB 2310860

**A**

10-09-1997

US

5780545 A

14-07-1998

DE

19709252 A

30-10-1997